


Beschreibung	Taschenfiltermedium	
General Information	Pocket filter media	
Anwendungsempfehlung	Recommendation for application	M5
Faserzusammensetzung	Fibre composition	100% Polypropylen
Flächengewicht WSP 130.1	Basis-Weight WSP 130.1	78 g/m ²
Dicke (0,008 N/cm²) in Anlehnung an WSP 120.6	Thickness (0,008 N/cm²) according to WSP 120.6	2,0 mm
Luftdurchlässigkeit (200 Pa) WSP 70.1	Air Permeability (200 Pa) WSP 70.1	1.200 l/m ² /s
Druckdifferenz (0,16 m/s) WSP 70.1	Initial pressure drop (0,16 m/s) WSP 70.1	25 Pa
Abscheideleistung (0,4 µm) DIN EN 779	Initial efficiency (0,4 µm) DIN EN 779	15%
Brandverhalten DIN 53438	Flammability DIN 53438	K1 / F1 / F1

Druckdifferenz
Initial pressure drop



Abscheideleistung
Initial efficiency

